

COATING	SALT SPRAY	KESTERNICH	APPLICATION
Black Oxide	24 hrs.	n/a	Used indoors for dry, non-corrosive applications.
Black Phosphate	48 hrs.	n/a	Used indoors for dry, non-corrosive applications.
Clear Zinc	24 hrs.	n/a	Used indoors for dry, non-corrosive applications.
Yellow Zinc	24 hrs.	n/a	Used indoors and outdoors for dry, non-corrosive applications.
Dacrotized®	500 hrs.	n/a	Used outdoors for medium corrosive applications.
Ruspert®	1,000 hrs.	n/a	Used indoors and outdoors for high corrosive applications.
WAR®	1,000 hrs.	n/a	Used outdoors for high corrosive applications. ACQ compatible.
Strong-Shield®	1,000 hrs.	15 Cycles	Used outdoors for high corrosive applications. Acid rain protection. ACQ compatible.
410 Stainless Steel	n/a	n/a	Used outdoors for medium corrosive applications. ACQ compatible.
305 Stainless Steel	n/a	n/a	Used outdoors for high corrosive applications. ACQ compatible.