Test Results

| Pullout Values (Avg. Lbs.) | | | | | | | | | | |
|----------------------------|----|-------------|-----|-----|-----|----|-----|------|-----|--|
| Fastener | | Steel Gauge | | | | | | | | |
| Size | Pt | 20 | 18 | 16 | 14 | 12 | 1/8 | 3/16 | 1/4 | |
| 8-18 | 2 | 292 | 479 | 685 | 933 | | | | | |

| | | Shear Values (Avg. Lbs.) | | | | | | | | | |
|------|----------|--------------------------|----------------------|------|----|----|-----|------|-----|--|--|
| F | Fastener | | Steel Gauge (Lapped) | | | | | | | | |
| Size | Pt | 20 | 18 | 16 | 14 | 12 | 1/8 | 3/16 | 1/4 | | |
| 8-18 | 2 | 721 | 1031 | 1049 | | | | | | | |

The values listed are averages achieved under laboratory conditions and imply no warranty. Appropriate safety factors should be applied to these values for design purposes.

