

SET-3G™ High-Strength Epoxy Adhesive

SET-3G is the latest innovation in epoxy anchoring adhesives from Simpson Strong-Tie. Formulated to provide superior performance in cracked and uncracked concrete at elevated temperatures, SET-3G installs and performs in a variety of environmental conditions and temperature extremes. The exceptional bond strength of SET-3G results in high design strengths.

Features

- Exceptional performance — superior bond-strength values at even long-term elevated temperature of 110°F (43°C) using optimized drill bit diameters
- Tested in accordance with ICC-ES AC308 and ACI 355.4 for use in cracked and uncracked normal-weight and lightweight concrete
- Design flexibility — can be specified for dry or water-saturated conditions when in-service temperatures range from -40°F (-40°C) to 176°F (80°C)
- Jobsite versatility — can be installed in dry, water-saturated or water-filled holes in base materials with temperatures between 40°F (4°C) and 100°F (38°C)
- Maximized production and safety — qualified for installation using the Speed Clean™ DXS dust extraction drilling system as an alternative to the conventional blow-brush-blow hole-cleaning method
- Wire brush hole-cleaning system for conventional blow-brush-blow cleaning method
- Available in two cartridge configurations for maximum versatility — 8.5 oz. coaxial or 22 oz. side-by-side cartridges dispensed using manual, battery or pneumatic dispensing tools
- With higher bond strengths, ductile solutions can often be achieved with SET-3G in high seismic areas
- 1:1 ratio, two-component, high-strength, epoxy-based anchoring adhesive formula
- Two-year shelf life for unopened cartridges stored between 45°F (7°C) and 90°F (32°C)
- Low-odor formulation
- When properly mixed, SET-3G will be a uniform gray color
- Volatile organic compound (VOC) — 1.9 g/L
- Manufactured in the USA using global materials
- Tested per ACI355.4
- SET-3G code listed for installation with the Speed Clean™ DXS drill bits without any further cleaning (ICC-ES ESR-4057)

Applications

- Threaded rod anchor and rebar dowel installations in cracked and uncracked concrete under a wide variety of environmental installation and use conditions
- Installation in downward, horizontal and upwardly inclined (including overhead) orientations
- Qualified for use in structures assigned to Seismic Design Categories A through F

Codes

ICC-ES ESR-4057 (concrete); City of Los Angeles (see ICC-ES ESR-4057); AASHTO M235 and ASTM C881, Types I and IV, Grade 3, Class C; NSF/ANSI Standard 61 (300 in.² / 1,000 gal.)

Chemical Resistance

Contact Simpson Strong-Tie for information.



SET-3G Adhesive

Installation and Application Instructions

(See also pp. 100–102)

- Surfaces to receive epoxy must be clean per approved hole cleaning method.
- Base-material temperatures must be 40°F (4°C) or above at the time of installation. For best results, adhesive should be conditioned to a temperature between 70°F (21°C) and 80°F (37°C) at the time of installation.
- To warm cold adhesive, store cartridges in a warm, uniformly heated area or storage container. Do not immerse cartridges in water or use microwave to facilitate warming.
- Mixed material can harden in the dispensing nozzle within 30 minutes at 70°F (21°C).

Note: For full installation instructions, see product packaging or visit strongtie.com/set3g.

SET-3G™ High-Strength Epoxy Adhesive

SET-3G Adhesive Cartridge System

Model No.	Capacity (ounces)	Cartridge Type	Carton Quantity	Dispensing Tool(s)	Mixing Nozzle
SET3G10 ²	8.5	Coaxial	12	CDT10S	EMN22I
SET3G22-N ¹	22	Side-by-side	10	EDT22S, EDTA22P, EDTA22CKT	EMN22I

- One EMN21I mixing nozzle and one extension are supplied with each cartridge.
- Two EMN22I mixing nozzles and two nozzle extensions are supplied with each cartridge.
- Cartridge estimation guidelines are available at strongtie.com/apps.
- Use only Simpson Strong-Tie® mixing nozzles in accordance with Simpson Strong-Tie instructions. Modification or improper use of mixing nozzle may impair SET-3G adhesive performance.

SET-3G Cure Schedule^{1,2}

Concrete Temperature		Gel Time	Cure Time
(°F)	(°C)	(min.)	(hr.)
40	4	120	192
50	10	75	72
60	16	50	48
70	21	35	24
90	32	25	24
100	38	15	24

For SI: 1°F = (°C × 9/5) + 32.

- For water-saturated concrete and water-filled holes, the cure times should be doubled.
- For installation of anchors in concrete where the temperature is below 70°F (21°C), the adhesive must be conditioned to a minimum temperature of 70°F (21°C).


Test Criteria

Anchors installed with SET-3G adhesive have been tested in accordance with ICC-ES *Acceptance Criteria for Adhesive Anchors in Concrete Elements (AC308)*.

Property	Test Method	Result*
Consistency	ASTM C881	Passed, non-sag
Heat deflection	ASTM D648	147°F
Bond strength (moist cure)	ASTM C882	3,306 psi at 2 days
Water absorption	ASTM D570	0.13%
Compressive yield strength	ASTM D695	15,390 psi
Compressive modulus	ASTM D695	991,830 psi
Shore D durometer	ASTM D2240	84
Gel time	ASTM C881	52 minutes
Volatile Organic Compound (VOC)	—	1.9 g/L

*Material and curing conditions: 73 ± 2°F, unless otherwise noted.

SET-3G™ High-Strength Epoxy Adhesive

SET-3G Installation Information and Additional Data
for Threaded Rod and Rebar in Normal-Weight Concrete¹

Characteristic	Symbol	Units	Nominal Anchor Diameter d_a (in.) / Rebar Size						
			3/8 / #3	1/2 / #4	5/8 / #5	3/4 / #6	7/8 / #7	1 / #8	1 1/4 / #10
Installation Information									
Drill Bit Diameter for Threaded Rod	d_{hole}	in.	7/16	9/16	1 1/16	7/8	1	1 1/8	1 3/8
Drill Bit Diameter for Rebar	d_{hole}	in.	1/2	5/8	3/4	7/8	1	1 1/8	1 3/8
Maximum Tightening Torque	T_{inst}	ft.-lb.	15	30	60	100	125	150	200
Minimum Embedment Depth	$h_{ef, min}$	in.	2 3/8	2 3/4	3 1/8	3 1/2	3 3/4	4	5
Maximum Embedment Depth	$h_{ef, max}$	in.	7 1/2	10	12 1/2	15	17 1/2	20	25
Minimum Concrete Thickness	h_{min}	in.	$h_{ef} + 1 1/4$			$h_{ef} + 2d_{hole}$			
Critical Edge Distance	c_{ac}	in.	See footnote 2						
Minimum Edge Distance	c_{min}	in.	1 3/4						2 3/4
Minimum Anchor Spacing	s_{min}	in.	3						6

1. The information presented in this table is to be used in conjunction with the design criteria of ACI 318-14 and ACI 318-11.

2. $c_{ac} = h_{ef} (\tau_{k, uncr} / 1,160)^{0.4} \times [3.1 - 0.7(h/h_{ef})]$, where:

$$[h/h_{ef}] \leq 2.4$$

$\tau_{k, uncr}$ = the characteristic bond strength in uncracked concrete, given in the tables that follow $\leq k_{uncr} ((h_{ef} \times f'_c)^{0.5} / (\pi \times d_a))$


h = the member thickness (inches)

h_{ef} = the embedment depth (inches)

* See p. 13 for an explanation of the load table icons.

SET-3G™ Design Information — Concrete

SET-3G Tension Strength Design Data for Threaded Rod in Normal-Weight Concrete^{1, 8}



Adhesive Anchors

Characteristic	Symbol	Units	Nominal Rod Diameter (in.)									
			3/8	1/2	5/8	3/4	7/8	1	1 1/4			
Steel Strength in Tension												
Minimum Tensile Stress Area	A_{se}	in. ²	0.078	0.142	0.226	0.334	0.462	0.606	0.969			
Tension Resistance of Steel — ASTM F1554, Grade 36	N_{sa}	lb.	4,525	8,235	13,110	19,370	26,795	35,150	56,200			
Tension Resistance of Steel — ASTM F1554, Grade 55			5,850	10,650	16,950	25,050	34,650	45,450	72,675			
Tension Resistance of Steel — ASTM A193, Grade B7			9,750	17,750	28,250	41,750	57,750	75,750	121,125			
Tension Resistance of Steel — Stainless Steel ASTM A193, Grade B8 and B8M (Types 304 and 316)			4,445	8,095	12,880	19,040	26,335	34,540	55,235			
Tension Resistance of Steel — Stainless Steel ASTM F593 CW (Types 304 and 316)			7,800	14,200	22,600	28,390	39,270	51,510	82,365			
Tension Resistance of Steel — Stainless Steel ASTM A193, Grade B6 (Type 410)			8,580	15,620	24,860	36,740	50,820	66,660	106,590			
Strength Reduction Factor for Tension — Steel Failure	ϕ	—	0.75 ⁵									
Concrete Breakout Strength in Tension (2,500 psi ≤ f'_c ≤ 8,000 psi)												
Effectiveness Factor for Cracked Concrete	$k_{c,cr}$	—	17									
Effectiveness Factor for Uncracked Concrete	$k_{c,uncr}$	—	24									
Strength Reduction Factor — Concrete Breakout Failure in Tension	ϕ	—	0.65 ⁶									
Bond Strength in Tension (2,500 psi ≤ f'_c ≤ 8,000 psi)⁷												
Minimum Embedment	$h_{ef,min}$	in.	2 3/8	2 3/4	3 1/8	3 1/2	3 3/4	4	5			
Maximum Embedment	$h_{ef,max}$	in.	7 1/2	10	12 1/2	15	17 1/2	20	25			
Continuous Inspection	Temperature Range A ^{2,4}	Characteristic Bond Strength in Cracked Concrete ⁹	$\tau_{k,cr}$	psi	1,448	1,402	1,356	1,310	1,265	1,219	1,128	
		Characteristic Bond Strength in Uncracked Concrete ⁹	$\tau_{k,uncr}$	psi	2,357	2,260	2,162	2,064	1,967	1,868	1,672	
	Temperature Range B ^{3,4}	Characteristic Bond Strength in Cracked Concrete ⁹	$\tau_{k,cr}$	psi	1,201	1,163	1,125	1,087	1,050	1,012	936	
		Characteristic Bond Strength in Uncracked Concrete ⁹	$\tau_{k,uncr}$	psi	1,957	1,876	1,795	1,713	1,632	1,551	1,388	
	Anchor Category	Dry Concrete	—	—	1							
	Strength Reduction Factor	Dry Concrete	$\phi_{dry,ci}$	—	0.65 ¹⁰							
	Anchor Category	Water-Saturated Concrete, or Water-Filled Hole	—	—	3		2					
	Strength Reduction Factor	Water-Saturated Concrete, or Water-Filled Hole	$\phi_{wet,ci}$	—	0.45 ¹⁰		0.55 ¹⁰					
	Periodic Inspection	Temperature Range A ^{2,4}	Characteristic Bond Strength in Cracked Concrete ⁹	$\tau_{k,cr}$	psi	1,346	1,304	1,356	1,310	1,265	1,219	1,128
			Characteristic Bond Strength in Uncracked Concrete ⁹	$\tau_{k,uncr}$	psi	2,192	2,102	2,162	2,064	1,967	1,868	1,672
Temperature Range B ^{3,4}		Characteristic Bond Strength in Cracked Concrete ⁹	$\tau_{k,cr}$	psi	1,117	1,082	1,125	1,087	1,050	1,012	936	
		Characteristic Bond Strength in Uncracked Concrete ⁹	$\tau_{k,uncr}$	psi	1,820	1,744	1,795	1,713	1,632	1,551	1,388	
Anchor Category		Dry Concrete	—	—	2		1					
Strength Reduction Factor		Dry Concrete	$\phi_{dry,pi}$	—	0.55 ¹⁰		0.65 ¹⁰					
Anchor Category		Water-Saturated Concrete, or Water-Filled Hole	—	—	3							
Strength Reduction Factor		Water-Saturated Concrete, or Water-Filled Hole	$\phi_{wet,pi}$	—	0.45 ¹⁰							
Reduction Factor for Seismic Tension			$\alpha_{N,seis}$ ¹¹	—	1.0	0.9	1.0	1.0	1.0	1.0	1.0	

- The information presented in this table is to be used in conjunction with the design criteria of ACI 318-14 and ACI 318-11.
- Temperature Range A: Maximum short-term temperature = 160°F, maximum long-term temperature = 110°F.
- Temperature Range B: Maximum short-term temperature = 176°F, maximum long-term temperature = 110°F.
- Short-term concrete temperatures are those that occur over short intervals (diurnal cycling). Long-term temperatures are roughly constant over significant periods of time.
- The tabulated value of ϕ applies when the load combinations of ACI 318-14 5.3 or ACI 318-11 9.2 are used. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318-11 D.4.4 to determine the appropriate value of ϕ .
- The tabulated value of ϕ applies when both the load combinations of ACI 318-14 5.3, or ACI 318-11 9.2 are used and the requirements of ACI 318-14 17.3.3 (c) or ACI 318-11 D.4.3 (c), as applicable, for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318 D.4.4 (c) for Condition B to determine the appropriate value of ϕ .

- Bond strength values shown are for normal-weight concrete having a compressive strength of $f'_c = 2,500$ psi. For higher compressive strengths up to 8,000 psi, the tabulated characteristic bond strength may be increased by a factor of $(f'_c/2,500)^{0.35}$ for uncracked concrete and a factor of $(f'_c/2,500)^{0.24}$ for cracked concrete.
- For lightweight concrete, the modification factor for bond strength shall be as given in ACI 318-14 17.2.6 or ACI 318-11 D.3.6, as applicable, where applicable.
- Characteristic bond strength values are for sustained loads, including dead and live loads.
- The tabulated value of ϕ applies when both the load combinations of ACI 318-14 5.3, or ACI 318-11 9.2 are used and the requirements of ACI 318-14 17.3.3 (c) or ACI 318-11 D.4.3 (c), as applicable, for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318 D.4.4(c) for Condition B to determine the appropriate value of ϕ .
- For anchors installed in regions assigned to Seismic Design Category C, D, E or F, the bond strength values must be multiplied by $\alpha_{N,seis}$.

* See p. 13 for an explanation of the load table icons.

SET-3G™ Design Information — Concrete

SET-3G Tension Strength Design Data for Rebar in Normal-Weight Concrete^{1,8}



Characteristic		Symbol	Units	Rebar Size							
				#3	#4	#5	#6	#7	#8	#10	
Steel Strength in Tension											
Minimum Tensile Stress Area		A_{se}	in. ²	0.11	0.20	0.31	0.44	0.60	0.79	1.27	
Tension Resistance of Steel — Rebar (ASTM A615 Grade 60)		N_{sa}	lb.	9,900	18,000	27,900	39,600	54,000	71,100	114,300	
Tension Resistance of Steel — Rebar (ASTM A706 Grade 60)				8,800	16,000	24,800	35,200	48,000	63,200	101,600	
Strength Reduction Factor for Tension — Steel Failure		ϕ	—	0.75 ⁵							
Concrete Breakout Strength in Tension (2,500 psi ≤ f'_c ≤ 8,000 psi)											
Effectiveness Factor for Cracked Concrete		$k_{c,cr}$	—	17							
Effectiveness Factor for Uncracked Concrete		$k_{c,uncr}$	—	24							
Strength Reduction Factor — Concrete Breakout Failure in Tension		ϕ	—	0.65 ⁶							
Bond Strength in Tension (2,500 psi ≤ f'_c ≤ 8,000 psi)⁷											
Minimum Embedment		$h_{ef,min}$	in.	2¾	2¾	3½	3½	3¾	4	5	
Maximum Embedment		$h_{ef,max}$	in.	7½	10	12½	15	17½	20	25	
Continuous Inspection	Temperature Range A ^{2,4}	Characteristic Bond Strength in Cracked Concrete ⁹	$\tau_{k,cr}$	psi	1,448	1,402	1,356	1,310	1,265	1,219	1,128
		Characteristic Bond Strength in Uncracked Concrete ⁹	$\tau_{k,uncr}$	psi	2,269	2,145	2,022	1,898	1,774	1,651	1,403
	Temperature Range B ^{3,4}	Characteristic Bond Strength in Cracked Concrete ⁹	$\tau_{k,cr}$	psi	1,201	1,163	1,125	1,087	1,050	1,012	936
		Characteristic Bond Strength in Uncracked Concrete ⁹	$\tau_{k,uncr}$	psi	1,883	1,781	1,678	1,575	1,473	1,370	1,165
	Anchor Category	Dry Concrete	—	—	1						
	Strength Reduction Factor	Dry Concrete	$\phi_{dry,ci}$	—	0.65 ¹⁰						
	Anchor Category	Water-Saturated Concrete, or Water-Filled Hole	—	—	3		2				
	Strength Reduction Factor	Water-Saturated Concrete, or Water-Filled Hole	$\phi_{wet,ci}$	—	0.45 ¹⁰		0.55 ¹⁰				
Periodic Inspection	Temperature Range A ^{2,4}	Characteristic Bond Strength in Cracked Concrete ⁹	$\tau_{k,cr}$	psi	1,346	1,304	1,356	1,310	1,265	1,219	1,128
		Characteristic Bond Strength in Uncracked Concrete ⁹	$\tau_{k,uncr}$	psi	2,110	1,995	2,022	1,898	1,774	1,651	1,403
	Temperature Range B ^{3,4}	Characteristic Bond Strength in Cracked Concrete ⁹	$\tau_{k,cr}$	psi	1,117	1,082	1,125	1,087	1,050	1,012	936
		Characteristic Bond Strength in Uncracked Concrete ⁹	$\tau_{k,uncr}$	psi	1,751	1,656	1,678	1,575	1,473	1,370	1,165
	Anchor Category	Dry Concrete	—	—	2		1				
	Strength Reduction Factor	Dry Concrete	$\phi_{dry,pi}$	—	0.55 ¹⁰		0.65 ¹⁰				
	Anchor Category	Water-Saturated Concrete, or Water-Filled Hole	—	—	3						
	Strength Reduction Factor	Water-Saturated Concrete, or Water-Filled Hole	$\phi_{wet,pi}$	—	0.45 ¹⁰						
Reduction Factor for Seismic Tension		$\alpha_{N,seis}$ ¹¹	—	1.0	1.0	1.0	1.0	1.0	1.0	1.0	

- The information presented in this table is to be used in conjunction with the design criteria of ACI 318-14 and ACI 318-11.
- Temperature Range A: Maximum short-term temperature = 160°F, maximum long-term temperature = 110°F.
- Temperature Range B: Maximum short-term temperature = 176°F, maximum long-term temperature = 110°F.
- Short-term concrete temperatures are those that occur over short intervals (diurnal cycling). Long-term temperatures are roughly constant over significant periods of time.
- The tabulated value of ϕ applies when the load combinations of ACI 318-14 5.3 or ACI 318-11 9.2 are used. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318-11 D.4.4 to determine the appropriate value of ϕ .
- The tabulated value of ϕ applies when both the load combinations of ACI 318-14 5.3, or ACI 318-11 9.2 are used and the requirements of ACI 318-14 17.3.3 (c) or ACI 318-11 D.4.3 (c), as applicable, for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318 D.4.4(c) for Condition B to determine the appropriate value of ϕ .
- Bond strength values shown are for normal-weight concrete having a compressive strength of $f'_c = 2,500$ psi. For higher compressive strengths up to 8,000 psi, the tabulated characteristic bond strength may be increased by a factor of $(f'_c/2,500)^{0.36}$ for uncracked concrete and a factor of $(f'_c/2,500)^{0.25}$ for cracked concrete.
- For lightweight concrete, the modification factor for bond strength shall be as given in ACI 318-14 17.2.6 or ACI 318-11 D.3.6, as applicable, where applicable.
- Characteristic bond strength values are for sustained loads, including dead and live loads.
- The tabulated value of ϕ applies when both the load combinations of ACI 318-14 5.3, or ACI 318-11 9.2 are used and the requirements of ACI 318-14 17.3.3 (c) or ACI 318-11 D.4.3 (c), as applicable, for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318 D.4.4(c) for Condition B to determine the appropriate value of ϕ .
- For anchors installed in regions assigned to Seismic Design Category C, D, E or F, the bond strength values must be multiplied by $\alpha_{N,seis}$.

* See p. 13 for an explanation of the load table icons.

SET-3G™ Design Information — Concrete

SET-3G Shear Strength Design Data for Threaded Rod
in Normal-Weight Concrete¹

Characteristic	Symbol	Units	Nominal Rod Diameter (in.)						
			3/8	1/2	5/8	3/4	7/8	1	1 1/4
Steel Strength in Shear									
Minimum Shear Stress Area	A_{se}	in. ²	0.078	0.142	0.226	0.334	0.462	0.606	0.969
Shear Resistance of Steel — ASTM F1554, Grade 36	V_{sa}	lb.	2,715	4,940	7,865	11,625	16,080	21,090	33,720
Shear Resistance of Steel — ASTM F1554, Grade 55			3,510	6,390	10,170	15,030	20,790	27,270	43,605
Shear Resistance of Steel — ASTM A193, Grade B7			5,850	10,650	16,950	25,050	34,650	45,450	72,675
Reduction factor for Seismic Shear — Carbon Steel	$\alpha_{V_{seis}}^4$	—	0.75					1.0	
Shear Resistance of Steel — Stainless Steel ASTM A193, Grade B8 and B8M (Types 304 and 316)	V_{sa}	lb.	2,665	4,855	7,730	11,425	15,800	20,725	33,140
Shear Resistance of Steel — Stainless Steel ASTM F593 CW (Types 304 and 316)			4,680	8,520	13,560	17,035	23,560	30,905	49,420
Shear Resistance of Steel — Stainless Steel ASTM A193, Grade B6 (Type 410)			5,150	9,370	14,915	22,040	30,490	40,000	63,955
Reduction factor for Seismic Shear — Stainless Steel	$\alpha_{V_{seis}}^4$	—	0.80		0.75			1.0	
Strength Reduction Factor for Shear — Steel Failure	ϕ	—	0.65 ²						
Concrete Breakout Strength in Shear									
Outside Diameter of Anchor	d_a	in.	0.375	0.5	0.625	0.75	0.875	1	1.25
Load-Bearing Length of Anchor in Shear	l_e	in.	h_{ef}						
Strength Reduction Factor for Shear — Breakout Failure	ϕ	—	0.70 ³						
Concrete Pryout Strength in Shear/									
Load-Bearing Length of Anchor in Shear	k_{cp}	in.	1.0 for $h_{ef} < 2.50"$; 2.0 for $h_{ef} \geq 2.50"$						
Strength Reduction Factor for Shear — Breakout Failure	ϕ	—	0.70 ³						

1. The information presented in this table is to be used in conjunction with the design criteria of ACI 318-14 and ACI 318-11.

2. The tabulated value of ϕ applies when the load combinations of ACI 318-14 5.3 or ACI 318-11 9.2 are used. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318-11 D.4.4 to determine the appropriate value of ϕ .

3. The tabulated value of ϕ applies when both the load combinations of ACI 318-14 5.3, or ACI 318-11 9.2 are used and the requirements

of ACI 318-14 17.3.3 (c) or ACI 318-11 D.4.3 (c), as applicable, for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318 D.4.4 (c) for Condition B to determine the appropriate value of ϕ .

4. The values of V_{sa} are applicable for both cracked concrete and uncracked concrete. For anchors installed in regions assigned to Seismic Design Category C, D, E or F, V_{sa} must be multiplied by $\alpha_{V_{seis}}$ for the corresponding anchor steel type.

* See p. 13 for an explanation of the load table icons.

SET-3G™ Design Information — Concrete

SET-3G Shear Strength Design Data for Rebar in Normal-Weight Concrete¹



Characteristic	Symbol	Units	Nominal Rod Diameter (in.)						
			#3	#4	#5	#6	#7	#8	#10
Steel Strength in Shear									
Minimum Shear Stress Area	A_{se}	in. ²	0.110	0.200	0.310	0.440	0.600	0.790	1.270
Shear Resistance of Steel — Rebar (ASTM A615 Grade 60)	V_{sa}	lb.	5,940	10,800	16,740	23,760	32,400	42,660	68,580
Shear Resistance of Steel — Rebar (ASTM A706 Grade 60)			5,280	9,600	14,880	21,120	28,800	37,920	60,960
Reduction Factor for Seismic Shear — Rebar (ASTM A615 Grade 60)	$\alpha_{V_{seis}}^A$	—	0.60					0.8	
Reduction Factor for Seismic Shear — Rebar (ASTM A706 Grade 60)			0.60					0.8	
Strength Reduction Factor for Shear — Steel Failure	ϕ	—	0.65 ²						
Concrete Breakout Strength in Shear									
Outside Diameter of Anchor	d_a	in.	0.375	0.5	0.625	0.75	0.875	1	1.25
Load-Bearing Length of Anchor in Shear	l_e	in.	h_{ef}						
Strength Reduction Factor for Shear — Breakout Failure	ϕ	—	0.70 ³						
Concrete Pryout Strength in Shear									
Load-Bearing Length of Anchor in Shear	k_{cp}	in.	1.0 for $h_{ef} < 2.50"$; 2.0 for $h_{ef} \geq 2.50"$						
Strength Reduction Factor for Shear — Breakout Failure	ϕ	—	0.70 ³						

- The information presented in this table is to be used in conjunction with the design criteria of ACI 318-14 and ACI 318-11.
- The tabulated value of ϕ applies when the load combinations of ACI 318-14 5.3 or ACI 318-11 9.2 are used. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318-11 D.4.4 to determine the appropriate value of ϕ .
- The tabulated value of ϕ applies when both the load combinations of ACI 318-14 5.3 or ACI 318-11 9.2 are used and the requirements of

- ACI 318-14 17.3.3 (c) or ACI 318-11 D.4.3 (c), as applicable, for Condition B are met. If the load combinations of ACI 318-11 Appendix C are used, refer to ACI 318 D.4.4 (c) for Condition B to determine the appropriate value of ϕ .
- The values of V_{sa} are applicable for both cracked concrete and uncracked concrete. For anchors installed in regions assigned to Seismic Design Category C, D, E or F, V_{sa} must be multiplied by $\alpha_{V_{seis}}$ for the corresponding anchor steel type.

For additional load tables, visit strongtie.com/set3g.



Anchor Designer™ Software for ACI 318, ETAG and CSA

Simpson Strong-Tie® Anchor Designer software accurately analyzes existing design or suggests anchor solutions based on user-defined design elements in cracked and uncracked concrete conditions.

* See p. 13 for an explanation of the load table icons.